

KB5302

Cure incorporated Terpolymer

PROVISIONAL TECHNICAL DATA SHEET

TECHNICAL INFORMATION

FLUONOX® KB5302 is a 70.5% high fluorine fluoroelastomer terpolymer which consists of HFP, VDF and TFE. FLUONOX® KB5302 is Bisphenol AF cure incorporated fluoroelastomer. It is suitable for Extrusion process. It shows excellent fuel and chemical resistance than copolymers in polar fluids and oxygenated gasoline along with good permeation resistance.

TYPICAL PROPERTIES

Properties	Value	Unit	Method
Appearance	Off white slab		
Specific gravity at 23°C (73F)	1.85	gm/cm ³	ASTM D792
Mooney viscosity - ML (1+10)' at 121°C (250F)	33	MU	ASTM D1646
Solubility	Dissolves in ketone and esters		
Shelf stability at room temp.	Excellent		
Fluorine content	70.5	%	Internal NMR Method

Note – These are typical properties and not to be used for specification purpose

PACKAGING

Fluonox® KB5302 is available in 25kg box.

Fluonox®KB5302

STANDARD FORMULATION OF COMPOUND

Formulation	Value		
Fluonox®KB5302	100		
N-990 carbon black	30 phr	Thermax N-990	Cancarb Ltd.
Magnesium oxide	3 phr	Kyowamag 150	Kyowa Chemical Industry Co. Ltd.
Calcium hydroxide	6 phr	OMM-2	Ohmi Kagaku Kogyo Co., Ltd

MDR 12MIN AT 177°C (351F), ARC 0.5°

Properties	Value	Unit	Method
ML	1.5	lbf x in	ASTM D6601
MH	12.5	lbf x in	ASTM D6601
ts2	3.0	min	ASTM D6601
tc50	4.6	min	ASTM D6601
tc90	6.5	min	ASTM D6601

PHYSICAL PROPERTIES:

Press cure 10 min at 170°C (338F); Post cure 24 hours at 230°C (446F)

Properties	Value	Unit	Method
100% Modulus	3.5 (508)	MPa (psi)	ASTM D412
Tensile strength	11.0 (1595)	MPa (psi)	ASTM D412
Elongation at break	300	%	ASTM D412
Shore A Hardness	75	Points	ASTM D2240

COMPRESSION SET: 70 HOURS AT 200°C (392°F)

Properties	Value	Unit	Method
Compression Set	35	%	ASTM D395 Method B

Note- The values of properties mention in technical data sheet are tested with proprietary materials listed above. Equivalent chemicals can also be used, however under such case; there may be little variation in the value of properties.

Fluonox®KB5302

SAFETY AND HANDLING

Handling and processing of fluoroelastomer must be done in ventilated areas to prevent personnel exposure to the fumes liberated during curing or use of cured rubber at high temperature. During the process, some fumes may generate at high temperature which are harmful for human beings. Fumes should not be inhaled; eye and skin contact must be avoided. In case of skin contact flush skin with cold water immediately. In case of eye contact, flush with water immediately and seek medical help. Smoking tobacco or cigarettes should not be allowed in working area. Mixing agents that contain metallic particulate such as powdered aluminium can rapidly decompose at high temperature; therefore do not use metallic particulate as mixing agent. Fluoroelastomer should be stored away from heat. It should be kept in clean and dry area where it can be protected until it is used. Please read the Material Safety Data Sheet before handling the product.

FLUONOX® is the brand name of Gujarat Fluorochemicals Limited (GFL) used for its brand of fluoroelastomer. FLUONOX® can be used in applications duly approved by GFL. Customers who plan to use the word FLUONOX® as the trade mark on or relation to their own fluoroelastomer parts and other products in any style or combination or in any manner whatsoever must contact GFL for prior permission for such use. No consumer/user of GFL fluoropolymer resin is permitted to claim that their products contain FLUONOX® without prior permission from GFL.

The information provided in the bulletin is furnished at no cost to the recipient and is based on information and technical data that Gujarat Fluorochemicals Limited believes is correct and sound. Those who choose to use the information must be technically qualified, and do so entirely at their own cost and risk. The users must determine and insure that their specific conditions of processing present no health or safety hazards. GFL does not warranty, either expressly or impliedly in respect of use of this information for application of its FLUONOX® branded Fluoroelastomer and shall bear no liability as a result of any loss or damage caused directly or indirectly due to use of any information provided in this bulletin. Nothing contained herein can be taken or construed as a grant of license by GFL to operate under or a recommendation to infringe any patents.

Note warning: Do not use any of FLUONOX® Fluoroelastomer in medical devices that are designed for permanent implantation in the human body. For other medical uses, prior permission of GFL may be sought.

SALES AND TECHNICAL SUPPORT

Corporate & Marketing office:

Gujarat Fluorochemicals Limited
Inox Towers, Plot no. 17, Sector 16/A
Noida-202301, U.P., INDIA
Tel: +91-120-6149600
Fax: +91-120-6149610

Europe

Gujarat Fluorochemicals GmbH
Esplanade 40, 9th Floor
20354 Hamburg, Germany
+49 040 5582 395- 80

Works

Gujarat Fluorochemicals Limited
12/A, GIDC Dahej Industrial Estate.
Tehsil- Vagra, Distt. Bharuch-392230, Gujarat, INDIA
Website: www.fluonox.co.in; www.gfl.co.in
Email: contact@gfl.co.in

Americas

GFL Americas, LLC
1212 Corporate Dr., Suite-540,
Irving, TX 75038, USA
+1 512 446 7700

