

KR527LP

Peroxide curable Raw Terpolymer

TECHNICAL DATA SHEET

TECHNICAL INFORMATION

FLUONOX[®] KR527LP is a low viscosity, high fluorine (>70%) peroxide curable terpolymer designed to cater to the requirements of extrusion applications. The terpolymer is composed of HFP, VDF, and TFE. It can be cross-linked using organic peroxides in combination with a coagent. It provides excellent processability, mechanical strength, and chemical resistance along with low permeation, making it ideal for applications in fuel hoses, and EGR Lines in both conventional and blended fuels such as E10 and E20 and bio-diesel. It can be used also in compression, injection and transfer molding.

PRODUCT FEATURES

- Good Extrusion processability
- Effective bonding to other rubber materials and metal
- Very low fuel permeability, Excellent chemical resistance among fluoroelastomer
- High Elongation at break and low modulus combined with superior compression set

TYPICAL PROPERTIES

Properties	Nominal Value	Unit	Method
Appearance	Off white slab	-	-
Specific gravity at 23°C (73°F)	1.90	gm/cm ³	ASTM D792
Mooney viscosity ML (1+10)' at 121°C (250°F)	25	MU	ASTM D1646
Solubility	Dissolves in ketone and esters	-	-
Shelf stability at room temp.	Excellent	-	-
Fluorine content	70.4	%	Internal NMR Method

Note – These are typical properties and not to be used for specification purpose.

PACKAGING

Fluonox[®] KR527LP is available in 25kg box.

Fluonox® KR527LP

STANDARD FORMULATION OF COMPOUND

Formulation	Value		
Fluonox® KR527LP	100		
N-990 carbon black	30 phr	Thermax N-990	Cancarb Ltd.
TAIC (100%)	3 phr		
Luperox #101XL45	3 phr		Arkema
ZnO	5 phr		

MDR 6MIN AT 177°C (351°F), ARC 0.5°

Properties	Value	Unit	Method
ML	0.6	lbf x in	ASTM D6601
MH	20.0	lbf x in	ASTM D6601
ts2	0.60	min	ASTM D6601
tc50	0.7	min	ASTM D6601
tc90	1.1	min	ASTM D6601

PHYSICAL PROPERTIES:

Press cure 10 min at 170°C (338°F); Post cure 4 hours at 230°C (446°F)

Properties	Value	Unit	Method
100% Modulus	5.0 (725)	MPa (psi)	ASTM D412
Tensile strength	19 (2755)	MPa (psi)	ASTM D412
Elongation at break	260	%	ASTM D412
Shore A Hardness	73	Points	ASTM D2240

COMPRESSION SET: 70 HOURS AT 200°C (392°F)

Properties	Value	Unit	Method
Compression Set	33	%	ASTM D395 Method B

Note: The values of properties mentioned in the technical data sheet are tested with proprietary materials listed above. Equivalent chemicals can also be used, however under such a case; there may be a little variation in the value of properties..

Fluonox® KR527LP

SAFETY AND HANDLING

Handling and processing of fluoroelastomer must be done in ventilated areas to prevent personnel exposure to the fumes liberated during curing or use of cured rubber at high temperature. During the process, some fumes may generate at high temperature which are harmful for human beings. Fumes should not be inhaled; eye and skin contact must be avoided. In case of skin contact flush skin with cold water immediately. In case of eye contact, flush with water immediately and seek medical help. Smoking tobacco or cigarettes should not be allowed in working area. Mixing agents that contain metallic particulate such as powdered aluminium can rapidly decompose at high temperature; therefore do not use metallic particulate as mixing agent. Fluoroelastomer should be stored away from heat. It should be kept in clean and dry area where it can be protected until it is used. Please read the Material Safety Data Sheet before handling the product.

Disclaimer

FLUONOX® is the brand name of Gujarat Fluorochemicals Limited (GFL) used for its brand of fluoroelastomer. FLUONOX® can be used in applications duly approved by GFL. Customers who plan to use the word FLUONOX® as the trade mark on or relation to their own fluoroelastomer parts and other products in any style or combination or in any manner whatsoever must contact GFL for prior permission for such use. No consumer/user of GFL fluoropolymer resin is permitted to claim that their products contain FLUONOX® without prior permission from GFL.

The information provided in the bulletin is furnished at no cost to the recipient and is based on information and technical data that Gujarat Fluorochemicals Limited believes is correct and sound. Those who choose to use the information must be technically qualified, and do so entirely at their own cost and risk. The users must determine and insure that their specific conditions of processing present no health or safety hazards. GFL does not warranty, either expressly or impliedly in respect of use of this information for application of its FLUONOX® branded Fluoroelastomer and shall bear no liability as a result of any loss or damage caused directly or indirectly due to use of any information provided in this bulletin. Nothing contained herein can be taken or construed as a grant of license by GFL to operate under or a recommendation to infringe any patents.

Note warning

Do not use any of FLUONOX® Fluoroelastomer in medical devices that are designed for permanent implantation in the human body. For other medical uses, prior permission of GFL may be sought.

SALES AND TECHNICAL SUPPORT

Corporate & Marketing office:

Gujarat Fluorochemicals Limited
Inox Towers, Plot no. 17, Sector 16/A
Noida-201301, U.P., INDIA
Tel: +91-120-6149600
Fax: +91-120-6149610

Europe

Gujarat Fluorochemicals GmbH
Esplanade 40, 9th Floor
20354 Hamburg, Germany
+49 040 5582 395- 80

Works

Gujarat Fluorochemicals Limited
12/A, GIDC Dahej Industrial Estate.
Tehsil- Vagra, Distt. Bharuch-392130, Gujarat, INDIA
Website: www.fluonox.co.in; www.gfl.co.in
Email: contact@gfl.co.in

Americas

GFL Americas, LLC
1212 Corporate Dr., Suite-540,
Irving, TX 75038, USA
+1 512 446 7700

