

KR630
Raw gum Terpolymer

TECHNICAL DATA SHEET

TECHNICAL INFORMATION

FLUONOX[®] KR630 is a fluoroelastomer that consists of HFP, VDF and TFE. It does not contain curatives, it can be cured with diamine or bisphenol AF curing systems. FLUONOX[®] KR630 exhibits the best low temperature properties among standard Fluoroelastomer, with a TR10 of -19°C. It is suitable for injection and transfer moulding. FLUONOX[®] KR630 grade is an excellent choice for making O-rings, seals and gaskets where better low temperature properties versus copolymers are required.

PRODUCT FEATURES

- Improved low temperature property vs. standard copolymers
- Good chemical resistance
- Good Compression set resistance
- Good mould release

TYPICAL PROPERTIES

Properties	Nominal Value	Unit	Test Method
Appearance	Off white slab	-	-
Specific gravity at 23°C (73°F)	1.82	gm/cm ³	ASTM D792
Mooney viscosity ML (1+10)' at 121°C (250°F)	30	MU	ASTM D1646
Solubility	Dissolves in ketone and esters	-	-
Shelf stability at room temp.	Excellent	-	-
Fluorine content	65.8	%	Internal NMR method

Note: These are typical properties and not to be used for specification purposes.

PACKAGING

FLUONOX[®] KR630 is available in 25 kg box.

Fluonox® KR630

STANDARD FORMULATION OF COMPOUND

Formulation	Value		
FLUONOX® KR630	100		
Bisphenol AF	2.0 phr		GFL
BTPPC	0.5 phr		GFL
N-990 carbon black	30 phr	Thermax N-990	Cancarb Ltd.
Magnesium oxide	3 phr	Kyowamag 150	Kyowa Chemical Industry Co. Ltd.
Calcium hydroxide	6 phr	OMM-2	Ohmi Kagaku Kogyo Co., Ltd

MDR 6MIN AT 177°C (351°F), ARC 0.5°

Properties	Value	Unit	Test Method
ML	0.9	lbf x in	ASTM D6601
MH	21.0	lbf x in	ASTM D6601
ts2	1.3	min	ASTM D6601
tc50	1.6	min	ASTM D6601
tc90	2.6	min	ASTM D6601

PHYSICAL PROPERTIES

Press cure 10 min at 170°C (338°F); Post cure 24 hours at 230°C (446°F)

Properties	Value	Unit	Test Method
100% Modulus	8.0 (1160)	MPa (psi)	ASTM D412
Tensile strength	13.0 (1885)	MPa (psi)	ASTM D412
Elongation at break	170	%	ASTM D412
Shore A Hardness	75	Points	ASTM D2240

LOW TEMPERATURE PROPERTIES

Properties	Value	Unit	Test Method
TR10	-19	°C	ASTM D1329

COMPRESSION SET: 70 HOURS AT 200°C (392°F)

Properties	Value	Unit	Test Method
Compression set	19	%	ASTM D395 Method B

Note: The values of properties mentioned in the technical data sheet are tested with proprietary materials listed above. Equivalent chemicals can also be used, however under such a case; there may be a little variation in the value of properties.

Fluonox® KR630

SAFETY AND HANDLING

Handling and processing of fluoroelastomer must be done in ventilated areas to prevent personnel exposure to the fumes liberated during curing or use of cured rubber at high temperatures. During the process, some fumes may generate at high temperatures which are harmful to human beings. Fumes should not be inhaled; eye and skin contact must be avoided. In case of skin contact flush skin with cold water immediately. In case of eye contact, flush with water immediately and seek medical help. Smoking tobacco or cigarettes should not be allowed in the working area. Mixing agents that contain metallic particulate such as powdered Aluminium can rapidly decompose at high temperatures; therefore do not use metallic particulate as a mixing agent. Fluoroelastomer should be stored away from heat. It should be kept in a clean and dry area where it can be protected until it is used. Please read the Material Safety Data Sheet before handling the product.

Disclaimer

FLUONOX® is the brand name of Gujarat Fluorochemicals Limited (GFL) used for its brand of fluoroelastomer. FLUONOX® can be used in applications duly approved by GFL. Customers who plan to use the word FLUONOX® as the trademark on or relation to their fluoroelastomer parts and other products in any style or combination or any manner whatsoever must contact GFL for prior permission for such use. No consumer/user of GFL fluoroelastomer is permitted to claim that their products contain FLUONOX® without prior permission from GFL.

The information provided in the bulletin is furnished at no cost to the recipient and is based on the information and technical data that Gujarat Fluorochemicals Limited believes is correct and sound. Those who choose to use the information must be technically qualified, and do so entirely at their own cost and risk. The users must determine and ensure that their specific conditions of processing present no health or safety hazards. GFL does not warranty, either expressly or impliedly in respect of the use of this information for application of its FLUONOX® branded fluoroelastomer and shall bear no liability as a result of any loss or damage caused directly or indirectly due to use of any information provided in this bulletin. Nothing contained herein can be taken or construed as a grant of license by GFL to operate under or a recommendation to infringe any patents..

Warning: Do not use any of FLUONOX® Fluoroelastomer in medical devices that are designed for permanent implantation in the human body. For other medical uses, prior permission of GFL may be sought.

SALES AND TECHNICAL SUPPORT

Corporate & Marketing office:

Gujarat Fluorochemicals Limited

INOXGFL Towers, Plot no. 17, Sector 16A

Noida-201301, U.P., INDIA

Tel: +91-120-6149600

Fax: +91-120-6149610

Europe

Gujarat Fluorochemicals GmbH

Esplanade 40, 9th Floor

20354 Hamburg, Germany

+49 040 5582 395- 80

Works

Gujarat Fluorochemicals Limited

12/A, GIDC Dahej Industrial Estate.

Tehsil- Vagra, Distt. Bharuch-392130, Gujarat, INDIA

Website: www.fluonox.co.in; www.gfl.co.in

Email: contact@gfl.co.in

Americas

GFL Americas, LLC

1212 Corporate Dr., Suite-540,

Irving, TX 75038, USA

+1 512 446 7700

